

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

Amendments to the Claims:

This listing of claims replaces all prior versions and listings of claims in the application:

Listing of Claims:

Claim 1. (Withdrawn) A method of joining a surface of a first ceramic component to a surface of a second ceramic component using a silver-based composition, the silver-based composition being a mixture of silver metal and a metal oxide, in which the metal in the metal oxide is a metal other than silver, the method comprising:

applying the silver-based composition to the surface of the first ceramic component;
applying the silver-based composition to the surface of the second ceramic component;
contacting the silver-based composition applied to the first ceramic component to the silver-based composition applied to the second ceramic component;

heating the surfaces of the first and second ceramic components to melt the applied silver-based compositions; and

cooling the surfaces of the first and second ceramic components to form a bond between the first and second ceramic components.

Claim 2. (Withdrawn) The method of claim 1 in which the first ceramic component comprises a varistor.

Claim 3. (Withdrawn) The method of claim 2 in which the second ceramic component comprises a varistor.

Claim 4. (Withdrawn) The method of claim 1 in which the first ceramic component comprises a metal oxide varistor.

Claim 5. (Withdrawn) The method of claim 4 in which the second ceramic component comprises a metal oxide varistor.

Claim 6. (Withdrawn) The method of claim 1 in which applying the silver-based composition to the surface of the first ceramic component includes:

preparing a powder of the metal oxide;
mixing the prepared metal oxide powder to form a metal oxide paste;
applying a foil of silver metal to the surface of the first ceramic component; and
spreading the metal oxide paste onto the applied silver foil to obtain the silver-based composition.

Claim 7. (Withdrawn) The method of claim 1 in which the silver-based composition melts at a temperature less than melting points of the first and second ceramic components.

Claim 8. (Withdrawn) The method of claim 7 in which the silver-based composition melts between around 900° Celsius and 1000° Celsius.

Claim 9. (Withdrawn) The method of claim 1 in which the silver-based composition is a mixture of silver metal and vanadium oxide.

Claim 10. (Withdrawn) The method of claim 9 in which the mixture comprises between around 0.1 to around 10% vanadium oxide by weight.

Claim 11. (Withdrawn) The method of claim 1 further comprising compressing the first and second ceramic components together before heating the surfaces of the ceramic components.

Claim 12. (Withdrawn) The method of claim 1 in which applying the silver-based composition to the surface of the first ceramic component includes:
preparing the metal oxide and the silver metal;
mixing the prepared metal oxide and the prepared silver metal to form a silver-based composition paste; and
spreading the silver-based composition paste on the first ceramic component to obtain the silver-based composition.

Claim 13. (Withdrawn) The method of claim 1 in which heating the surfaces of the first and second ceramic components comprises heating while in an air atmosphere or in a near air atmosphere.

Claim 14. (Currently amended) A method of joining a surface of a first ceramic component to a surface of a second ceramic component ~~using a silver-based composition, the silver-based composition being a mixture of silver metal and a metal oxide, in which the metal in the metal oxide is a metal other than silver~~, the method comprising:

applying the a silver-based composition to the surface of the first ceramic component, the silver-based composition being a mixture of silver metal and a metal oxide, in which the metal in the metal oxide is a metal other than silver;

contacting the silver-based composition applied to the first ceramic component to the surface of the second ceramic component;

heating the surfaces of the first and second ceramic components to melt the applied silver-based composition; and

cooling the surfaces of the first and second ceramic components to form a bond between the first and second ceramic components.

Claim 15. (Original) The method of claim 14 in which the first ceramic component comprises a varistor.

Claim 16. (Original) The method of claim 15 in which the second ceramic component comprises a varistor.

Claim 17. (Original) The method of claim 14 in which the first ceramic component comprises a metal oxide varistor.

Claim 18. (Original) The method of claim 17 in which the second ceramic component comprises a metal oxide varistor.

Claim 19. (Original) The method of claim 14 in which applying the silver-based composition to the surface of the first ceramic component includes:

preparing a powder of the metal oxide;
mixing the prepared metal oxide powder to form a metal oxide paste;
applying a foil of silver metal to the surface of the first ceramic component; and
spreading the metal oxide paste onto the applied silver foil to obtain the silver-based composition.

Claim 20. (Original) The method of claim 14 in which the silver-based composition melts at a temperature less than melting points of the first and second ceramic components.

Claim 21. (Original) The method of claim 20 in which the silver-based composition melts between around 900° Celsius and 1000° Celsius.

Claim 22. (Original) The method of claim 14 in which the silver-based composition is a mixture of silver metal and vanadium oxide.

Claim 23. (Original) The method of claim 22 in which the mixture comprises between approximately 0.1 to approximately 10% vanadium oxide by weight.

Claim 24. (Original) The method of claim 14 further comprising compressing the first and second ceramic components together before heating the surfaces of the ceramic components.

Claim 25. (Original) The method of claim 14 in which applying the silver-based composition to the surface of the first ceramic component includes:

- preparing the metal oxide and the silver metal;
- mixing the prepared metal oxide and the prepared silver metal to form a silver-based composition paste; and
- spreading the silver-based composition paste on the first ceramic component to obtain the silver-based composition.

Claim 26. (Original) The method of claim 14 in which heating the surfaces of the first and second ceramic components comprises heating while in an air atmosphere or in a near air atmosphere.

Claim 27. (Withdrawn) A bonded component stack for use in a surge arrester, the stack comprising:

- a first ceramic component having a surface;
- a second ceramic component having a surface;
- a silver-based composition brazed to the surfaces of the first and second ceramic components to bond the surface of the first ceramic component to the surface of the second ceramic component, the silver-based composition being a mixture of silver metal and a metal oxide, in which the metal in the metal oxide is a metal other than silver.

Claim 28. (Withdrawn) The stack of claim 27 in which the first ceramic component comprises a varistor.

Claim 29. (Withdrawn) The stack of claim 28 in which the second ceramic component comprises a varistor.

Claim 30. (Withdrawn) The stack of claim 27 in which the first ceramic component comprises a metal oxide varistor.

Claim 31. (Withdrawn) The stack of claim 30 in which the second ceramic component comprises a metal oxide varistor.

Claim 32. (Withdrawn) The stack of claim 27 in which the silver-based composition is brazed between the surfaces of the first and second ceramic components by applying the silver-based composition to the surface of the first ceramic component; contacting the silver-based composition applied to the first ceramic component to the surface of the second ceramic component; heating the surfaces of the first and second ceramic components to melt the applied silver-based composition; and cooling the surfaces of the first and second ceramic components to form a bond between the first and second ceramic components.

Claim 33. (Withdrawn) The stack of claim 27 in which the silver-based composition is brazed between the surfaces of the first and second ceramic components by compressing the first and second ceramic components together before heating the surfaces of the ceramic components.

Claim 34. (Withdrawn) The stack of claim 27 in which the silver-based composition is brazed between the surfaces of the first and second ceramic components by applying the silver-based composition to the surface of the first ceramic component; applying the silver-based

composition to the surface of the second ceramic component; contacting the silver-based composition applied to the first ceramic component to the silver-based composition applied to the second ceramic component; heating the surfaces of the first and second ceramic components to melt the applied silver-based compositions; and cooling the surfaces of the first and second ceramic components to form a bond between the first and second ceramic components.

Claim 35. (Withdrawn) The stack of claim 34 in which the silver-based composition is brazed between the surfaces of the first and second ceramic components by compressing the first and second ceramic components together before heating the surfaces of the ceramic components.

Claim 36. (Withdrawn) The stack of claim 27 in which the silver-based composition melts at a temperature less than melting points of the first and second ceramic components.

Claim 37. (Withdrawn) The stack of claim 36 in which the silver-based composition melts between around 900° Celsius and 1000° Celsius.

Claim 38. (Withdrawn) The stack of claim 27 in which the silver-based composition is a mixture of silver metal and vanadium oxide.

Claim 39. (Withdrawn) The stack of claim 38 in which the mixture comprises between around 0.1 to around 10% vanadium oxide by weight.

Claim 40. (Currently amended) A method of joining a first ceramic component to a second ceramic component ~~using a silver-based composition, the silver-based composition being a mixture of silver metal and a metal oxide, in which the metal in the metal oxide is a metal other than silver,~~ the method comprising:

placing ~~the~~ a silver-based composition between the first ceramic component and the second ceramic component, the silver-based composition being a mixture of silver metal and a metal oxide, in which the metal in the metal oxide is a metal other than silver;

joining the first ceramic component to the second ceramic component;
heating the first and second ceramic components to melt the silver-based composition;
and
cooling the first and second ceramic components to form a bond between the first and second ceramic components.

Claim 41. (Previously presented) The method of claim 14 in which contacting includes contacting the silver-based composition applied to the first ceramic component to a bare surface of the second component.

Claim 42. (Withdrawn) The method of claim 14 in which contacting includes contacting the silver-based composition applied to the first ceramic component to a surface of the second component that is coated with the silver-based composition.